

# Uniflon HIPERCONDUX 9 - GMP

Polytetrafluoroethylene

UNIFLON

## Message:

Uniflon HIPERCONDUX 9-GMP is a polytetrafluoroethylene (PTFE) product. It can be processed by sintering or injection molding and is available in North America or Latin America.

General Information			
Additive	Unspecified additive		
Features	Good liquidity		
Processing Method	Sintering		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.03 - 2.08	g/cm <sup>3</sup>	Internal method
Apparent Density	0.45 - 0.55	g/cm <sup>3</sup>	Internal method
Contractility-Sintering	3.0 - 5.0	%	Internal method
Sintering Temperature - Maximum	365	°C	
Flow time-50 grams	2.5 - 4.5	sec	Internal method

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	61 - 66		Internal method

Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	15.5	MPa	Internal method
Tensile Elongation (Break)	60	%	Internal method

Additional Information	Nominal Value	Unit	Test Method
Code: 010022002			

Injection	Nominal Value	Unit
Mold Temperature	21.0 - 25.0	°C
Injection Pressure	68.6 - 78.5	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT