ACRYLITE® Sheet Resist 45

Acrylic

Evonik Cyro LLC

Message:

Continuously manufactured ACRYLITE® Resist sheet is a versatile, thermoplastic material developed for the retail display and glazing markets as well as ther markets requiring strength, appearance and weatherability.

High optical quality ACRYLITE® Resist sheet provides the beautiful look of acrylic with much greater impact strength for durability during manufacturing, shipping, and in-store use. Rigid, tough, and lightweight, ACRYLITE® Resist is easily fabricated and machined, including cutting, routing, forming, and cementing.

ACRYLITE® Resist is ideal for use in: P-O-P Displays Store Fixtures Glazing General Fabrication

| General Information | | | | |
|--------------------------------|--------------------------|-------|-------------|--|
| Features | Good Chemical Resistance | | | |
| | Good Toughness | | | |
| | Good Weather Resistance | | | |
| | High Impact Resistance | | | |
| | High Rigidity | | | |
| | Machinable | | | |
| | | | | |
| Uses | Displays | | | |
| | Glazing | | | |
| | | | | |
| Appearance | Clear/Transparent | | | |
| Forms | Sheet | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.18 | g/cm³ | ASTM D792 | |
| Water Absorption (23°C, 24 hr) | 0.30 | % | ASTM D570 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Rockwell Hardness (M-Scale) | 88 | | ASTM D785 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Modulus | 2760 | MPa | ASTM D638 | |
| Tensile Strength | 59.3 | MPa | ASTM D638 | |
| Tensile Elongation (Yield) | 5.8 | % | ASTM D638 | |
| Flexural Modulus | 2550 | MPa | ASTM D790 | |
| Flexural Strength | 101 | MPa | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact | 35 | J/m | ASTM D256 | |
| Gardner Impact | 2.26 | J | ASTM D3029 | |
| Thermal | Nominal Value | Unit | Test Method | |

| Deflection Temperature Under Load (1.8 | | | |
|--|----------------------|----------|-----------------------|
| MPa, Unannealed) | 98.0 | °C | ASTM D648 |
| Vicat Softening Temperature | 103 | °C | ASTM D1525 |
| CLTE - Flow | 7.2E-5 | cm/cm/°C | ASTM D696 |
| | | | |
| Optical | Nominal Value | Unit | Test Method |
| Optical Gardner Gloss (20°) | Nominal Value 125 | Unit | Test Method ASTM D523 |
| | | Unit | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

