

KumhoSunny PC/PBT HCB9240

Polycarbonate + PBT

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HCB9240 is a high flow and high heat resistance PC/PBT alloy resin, offering high impact and excellent chemical resistance.HCB9240 is recommended for auto outside laggage carrier,handle, ectron & electric parts etc.

General Information			
Features	Good Chemical Resistance		
	High Flow		
	Medium Heat Resistance		
	Ultra High Impact Resistance		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
	Household Goods		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	20	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	1.2 to 1.5	%	ASTM D955
--	1.2 to 1.5	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	46.0	MPa	ASTM D638, ISO 527-2/50
Tensile Elongation (Break)	130	%	ASTM D638
Flexural Modulus			
--	1800	MPa	ASTM D790
-- ¹	1800	MPa	ISO 178
Flexural Strength			
--	75.0	MPa	ASTM D790
-- ²	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	15	kJ/m ²	

23°C	45	kJ/m²	
Notched Izod Impact			
3.20 mm	800	J/m	ASTM D256
23°C	40	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	86.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	98.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	230 to 260	°C	
Middle Temperature	240 to 270	°C	
Front Temperature	240 to 270	°C	
Nozzle Temperature	245 to 265	°C	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	50.0 to 80.0	°C	
Back Pressure	0.300 to 1.00	MPa	
Screw Speed	30 to 70	rpm	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT