

Vexel PBT B50GF30

Polybutylene Terephthalate

Custom Resins Group

Message:

High-flow 30% glass fiber reinforced PBT polyester resin
Has the high chemical and heat resistance of PBT combined with high strength and stiffness
Suitable for levers, electrical connectors, housings and other parts which have long flow lengths or thin wall sections

General Information	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight
Features	Good Chemical Resistance
	High Flow
	High Heat Resistance
	High Stiffness
	High Strength
Uses	Connectors
	Housings
	Thin-walled Parts

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	117	MPa	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	207	°C	
1.8 MPa, Unannealed	202	°C	
Peak Melting Temperature	227	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

