

INSTRUC PCPETGF10

Polycarbonate + PET

Infinity LTL Engineered Compounds

Message:

INSTRUC PCPETGF10 is a Polycarbonate + PET (PC+PET) product filled with 10% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.50	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	79.2	MPa	ASTM D638
Tensile Elongation (Yield)	3.0 to 5.0	%	ASTM D638
Flexural Modulus	4830	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	138	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	266 to 277	°C	
Mold Temperature	65.6 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT