

POLYTROPE® STR 3570EU-01 CLEAR

Enhanced Polyolefin (Capstock Resin)

A. Schulman Inc.

Message:

POLYTROPE STR 3570EU resin is a high gloss, non-stress whitening, weatherable, olefin cap resin providing exceptional durability. It is specifically designed for the co-extrusion process as a cap resin over ethylene base resins such as HMWPE. It is especially suited for thermoformed applications, as it maintains its' clarity, DOI, and high gloss through the thermoforming process. POLYTROPE STR 3570EU-01 CLEAR can be used as a clear cap or it can be easily colored. The high clarity, gloss and durability of the cap resin enables it to provide an economical solution to produce high gloss appearance parts in HMWPE.

General Information			
Features	Durable		
	Good Chemical Resistance		
	Good Weather Resistance		
	High Clarity		
	Low Temperature Impact Resistance		
	Recyclable Material		
	Scratch Resistant		
	Stain Resistant		
	Stress Whitening Resistant		
Forms	Pellets		
Processing Method	Coextrusion		
	Extrusion		
	Profile Extrusion		
	Sheet Extrusion		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	0.928	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.79	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ² (Yield, 23°C)	16.5	MPa	ISO 527-2
Tensile Strain ³ (Break, 233°C)	250	%	ISO 527-2
Flexural Modulus - Chord ⁴ (23°C)	379	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Instrumented Dart Impact (-30°C, Total Energy, Ductile Failure)	38.4	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	54.4	°C	ISO 75-2/Bf

Flammability	Nominal Value	Test Method
Flame Rating (3.18 mm, All Colors)	HB	UL 94
Optical	Nominal Value	Test Method
Gardner Gloss (60°, 3180 µm, Thermoformed, Smooth)	50 to 70	ISO 2813
NOTE		
1.	Method A	
2.	Type 1, 50 mm/min	
3.	Type 1, 50 mm/min	
4.	Type 1A, 2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

