

TROSIFOL® VG FR

Polyvinyl Butyral
Kuraray Co., Ltd.

Message:

Standard product for all laminating processes without stretching

General Information			
Uses	Automotive Applications		
	Laminates		
Appearance	Blue-Green		
	Clear/Transparent		
	Light Green		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm³	DIN 53479
Films	Nominal Value	Unit	Test Method
Tensile Strength	> 23.0	MPa	ISO 527-3
Tensile Elongation (Break)	> 280	%	ISO 527-3
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	2.2E-4	cm/cm/°C	ISO 11359-2
Specific Heat	1850	J/kg/°C	ISO 11357-4
Thermal Conductivity	0.20	W/m/K	DIN EN 12939
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+11	ohms	DIN 53482

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT