

Plaslube® PA6/6 GF33 TS15

Polyamide 66
Techmer Engineered Solutions

Message:

Plaslube®PA6/6 GF33 TS15 is a polyamide 66 (nylon 66) product, which contains a 33% glass fiber reinforced material. It can be processed by injection molding and is available in North America.

Features include:

flame retardant/rated flame

Lubrication

Wear-resistant

heat stabilizer

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 33% filler by weight		
Additive	PTFE lubricant (15%)		
	Silicone lubricant		
	heat stabilizer		
Features	Low friction coefficient		
	Good wear resistance		
	Thermal Stability		
	Lubrication		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.50	%	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	148	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength	222	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
With steel-dynamic	0.25		ASTM D1894
With steel-static	0.20		ASTM D1894
Wear Factor	36	10 ⁻⁸ mm ³ /N · m	
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	259	°C	ASTM D648
1.8 MPa, not annealed	254	°C	ASTM D648
CLTE - Flow	1.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength ¹	22	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (11.5 mm)	HB		UL 94
Additional Information	Nominal Value	Unit	

170001000 fpm

19000100 fpm

Limiting Pressure Velocity	1700010 fpm	psi-ft/min
Injection	Nominal Value	Unit
Drying Temperature	82.2	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	282 - 293	°C
Middle Temperature	288 - 299	°C
Front Temperature	277 - 288	°C
Nozzle Temperature	271 - 304	°C
Processing (Melt) Temp	282 - 304	°C
Mold Temperature	79.4 - 104	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.00 - 0.345	MPa

Injection instructions

Screw Speed: SlowRecommendations for Molding and Tool Conditions: Well vented moldMoisture Content, as received: Product is packaged at 0.2% or less.

NOTE

1. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

