

Witcom PES 6C/3L1

Polyethersulfone

Witcom Engineering Plastics B.V.

Message:

Witcom PES 6C/3L1 is a Polyethersulfone (PESU) product filled with 30% carbon fiber. It is available in Europe.

Characteristics include:

Flame Rated

Conductive

Lubricated

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Conductive		
	Lubricated		

Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Molding Shrinkage - Flow (3.00 mm)	0.10 to 0.30	%	ISO 2577
Water Absorption			ISO 62
Saturation, 23°C	1.4	%	
Equilibrium, 23°C, 50% RH	0.50	%	

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	< 150	MPa	ISO 527-2
Tensile Strain (Break)	1.0 to 2.0	%	ISO 527-2
Flexural Modulus	14500	MPa	ISO 178
Flexural Stress	220	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	6.5	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	20	kJ/m ²	ISO 180/1U

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	210	°C	ISO 75-2/A
CLTE - Flow	1.2E-5	cm/cm/°C	ISO 11359-2
RTI Imp (3.00 mm)	180	°C	UL 746

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 to 1.0E+3	ohms	ASTM D257
Volume Resistivity	10 to 1.0E+3	ohms · cm	ASTM D257

Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-0		ISO 1210
Glow Wire Flammability Index (1.60 mm)	960	°C	IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

