

INSTRUC PPSLGF10

Polyphenylene Sulfide
Infinity LTL Engineered Compounds

Message:
10% GLASS FIBER REINFORCED LINEAR POLYPHENYLENE SULFIDE

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	86.2	MPa	ASTM D638
Tensile Elongation (Break)	1.0 to 3.0	%	ASTM D638
Flexural Modulus	6210	MPa	ASTM D790
Flexural Strength	134	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Unnotched Izod Impact	110 to 210	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	260	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	321 to 332	°C	
Mold Temperature	135 to 177	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	7.6E-3 to 0.013	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

