

Tool-A-Thane UT-605

Polyurethane
Urethane Tooling & Engineering Corp

Message:

35% Deflection for optimum life
Hardness 65 Shore A
Low loadbearing capacity
Best for extremely light gages and extremely soft materials.

General Information			
Uses	Molds/Dies/Tools		
Physical	Nominal Value	Unit	
Specific Gravity	1.22	g/cm ³	
Molding Shrinkage - Flow	1.5	%	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore A)	65		
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction ¹ (vs. Steel - Dynamic)	> 0.80		
Abrasion Resistance - NBS Index	< 50.0		
Graves Tear	48.2	kN/m	
Penetration Depth - Recommended for optimum life	40	%	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
100% Strain	2.24	MPa	
300% Strain	5.86	MPa	
Tensile Strength	37.2	MPa	
Tensile Elongation (Break)	470	%	
Tear Strength (Split)	7.9	kN/m	ASTM D470
Thermal	Nominal Value	Unit	
Brittleness Temperature	-67.8	°C	
NOTE			

1. at 20 lbs load at 52 fpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

