# **BMC T15(F)**

### Thermoset Polyester

Bulk Molding Compounds, Inc.

### Message:

BMC T15(F) is a thermosetting polyester product. It is available in North America. Typical application areas are: electrical/electronic applications. The main characteristics are: flame retardant/rated flame.

General Information			
Uses	Electrical/Electronic Applications		
Appearance	Black		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.95	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	35		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	59.2	MPa	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength (Yield)	117	MPa	ASTM D790
Compressive Strength	140	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	360	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	16	kV/mm	ASTM D149
Arc Resistance	187	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.52 mm	V-0		UL 94
2.22 mm	V-0		UL 94
3.11 mm	V-0		UL 94
Additional Information			

Barcol Hardness, ASTM D2583: 30 to 40UL Flame Rating, UL 94, 0.058 to 0.062 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.120 to 0.125 in: V-OUL Flame Rating, UL 94, 0.058 to 0.062 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.1 in: V-OUL Flame Rating, UL 94, 0.075 to 0.125 in: V-OUL Flam

#### NOTE

1. Type 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

