

XYRON™ 644Z

Polyphenylene Ether + PS
Asahi Kasei Chemicals Corporation

Message:
Modified PPE
Unreinforced Flame retardant V-0
Heat resistance High

General Information			
UL YellowCard	E82268-100150215	E82268-633502	
Additive	Flame Retardant		
Features	Flame Retardant		
	High Heat Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183
Molding Shrinkage ¹ (2.00 mm)	0.50 to 0.80	%	Internal Method
Water Absorption (23°C, 24 hr)	0.10	%	ISO 62
Outdoor Suitability (Black)	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	74.0	MPa	ISO 527-2
Nominal Tensile Strain at Break (23°C)	9.0	%	ISO 527-2
Flexural Modulus (23°C)	2440	MPa	ISO 178
Flexural Stress (23°C)	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ² (23°C)	21	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	129	°C	ISO 75-2/A
CLTE - Flow (-30 to 65°C)	7.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec	125	°C	UL 746
RTI Imp	125	°C	UL 746
RTI Str	125	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
1.00 mm	V-0		
2.00 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	2.0 to 4.0	hr	

Processing (Melt) Temp	260 to 320	°C
Mold Temperature	60.0 to 100	°C
NOTE		
1.	150x150x2 mm	
2.	4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

