

Lytex 4084

Epoxy; Epoxide
Quantum Composites Inc.

Message:

Lytex 4084 is a high performance, glass fiber reinforced epoxy sheet molding compound designed for military and aerospace structural applications requiring excellent mechanical properties, retention of properties at elevated temperatures, good chemical resistance and excellent electrical properties. It is the 1-inch fiber version of Lytex 9063.

General Information			
Filler / Reinforcement	Glass Fiber,63% Filler by Weight		
Features	Good Chemical Resistance		
	Good Electrical Properties		
	High Heat Resistance		
Uses	Aerospace Applications		
	Military Applications		
Appearance	Black		
Forms	SMC - Sheet Molding Compound		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.85	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.050	%	ASTM D955
Water Absorption (24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	269	MPa	ASTM D638
Flexural Modulus	19300	MPa	ASTM D790
Flexural Strength	476	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2300	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	302	°C	ASTM D648
Continuous Use Temperature	177	°C	ASTM D794
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.0E+14	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (100 Hz)	4.30		ASTM D150
Dissipation Factor (100 Hz)	7.0E-3		ASTM D150
Thermoset	Nominal Value	Unit	
Shelf Life (-18°C)	26	wk	

Demold Time (138°C)

5.0 to 10

min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

