TEKNIFLEX® VPOA10200 ALU

PVC/PE/EVOH/PE/PCTFE Film

Tekni-Films, a div of Tekni-Plex

Message:

This data sheet describes TEKN|FLEX® VPOA 10200 ALU product

Tekni-Films offers a wide range of PVC / PE.EVOH.PE/PCTFE - based film structures to meet both performance and cost requirements of blister packaging of tablets, capsules, lozenges, and suppositories

General Information		
Uses	Pharmaceutical Packaging	
Agency Ratings	DMF 1378	
	FDA Unspecified Rating	
	USP Unspecified Rating	
Appearance	Aluminum	
Forms	Film	
Physical	Nominal Value	Unit
Specific Gravity	1.36	g/cm³
Dimensional Stability ¹ (140°C)	-4.0 to 4.0	%
Films	Nominal Value	Unit
Film Thickness ²	375	μm
Yield	1.96	m²/kg
Roll Width ³	< 106.70	cm
Thermoforming Molding Temperature	100 to 160	°C
Tensile Strength - MD (Yield)	37.9	MPa
Oxygen Transmission Rate (23°C, 100% RH)	0.47	cm³/m²/24 hr
Water Vapor Transmission Rate (38°C, 90% RH)	0.11	g/m²/24 hr
NOTE		
1.	30 minutes	
2.	Thickness tolerance: ±10%	
3.	Roll width tolerance: ±1.5 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

