

# Ebalta MG 804 / MG 804-1

Polyurethane

Ebalta Kunststoff GmbH

## Message:

This product is a polyurethane system.

The processing is preferably made in customary vacuum pouring plant.

Manual processing possible.

Maximum wall thicknesses of the parts: from 5 - 10 mm.

### Applications

High quality prototypes, like ABS

High quality prototypes, like PA

### Properties

long potlife

very well castable

good impact strength

easily dyeable

low aggressiveness against silicones

General Information			
Features	Good Colorability		
	Good Impact Resistance		
Uses	Prototyping		
Appearance	White		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage	0.10	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	73 to 77		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	44.0 to 60.0	MPa	ISO 527-2
Tensile Strain (Break)	10 to 14	%	ISO 527-2
Flexural Modulus	1830 to 2130	MPa	ISO 178
Flexural Stress	75.0 to 85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	25 to 37	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	79.0 to 85.0	°C	ISO 75-2/B
Glass Transition Temperature	87.0	°C	TMA
Thermoset	Nominal Value	Unit	
Thermoset Components			
Hardener	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Weight: 100		

Post Cure Time (60°C)	4.0	hr
Uncured Properties	Nominal Value	Unit
Density (20°C)	1.08 to 1.12	g/cm <sup>3</sup>
Curing Time (60°C)	0.75 to 1.0	hr
Pot Life <sup>1</sup> (20°C)	8.0 to 11	min
NOTE		
1.	200 g	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

