

Rilsan® AESNO P10 TL

Polyamide 12

Arkema

Message:

Rilsan® AESNO P10 TL is a Polyamide 12 (Nylon 12) product. It can be processed by blow molding or extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Good UV Resistance
- Heat Stabilizer
- Medium Viscosity
- Plasticized
- UV Stabilized

General Information			
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Good UV Resistance		
	Heat Stabilized		
	Medium Viscosity		
	Plasticized		
Appearance	Natural Color		
Forms	Pellets		
	Powder		
Processing Method	Blow Molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	0.30	%	
Saturation	0.70	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	68.9	MPa	ASTM D638
Tensile Elongation (Break)	330	%	ASTM D638
Flexural Modulus	758	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256

-40°C	32	J/m	
23°C	200	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	48.9	°C	ASTM D648
Melting Temperature	174	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

