

# Sumikon® PM-725 (Type: J Black)

Phenolic

SBHPP

Message:

SUMIKON PM-725 Type J Black is a Graphite molding compound based on Phenolic Novolac polymer. It is supplied in the form of Granular/Molding Powder for Molding.

General Information	
Filler / Reinforcement	Graphite fiber reinforced material
Appearance	Black
Forms	Powder
	Particles
Processing Method	Resin transfer molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm <sup>3</sup>	JIS K6911
Molding Shrinkage - Flow	0.30	%	JIS K6911
Water Absorption (Equilibrium)	0.030	%	JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	40.0	MPa	JIS K6911
Flexural Strength	65.0	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.6	kJ/m <sup>2</sup>	JIS K6911
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	170	°C	JIS K6911

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT