

# NYCOA Polyamide 4230 HST

Polyamide 6

Nycoa (Nylon Corporation of America)

Message:

NYCOA 4014 HST is a 14% glass fiber reinforced, heat stabilized, and translucent Nylon 6 resin used for injection molding. This grade features outstanding stiffness and dimensional stability.

NYCOA 4014 HST is available in UV stable, custom colors, and impact modified grades. It also has excellent chemical resistance to greases, oils, and other hydrocarbons.

NYCOA 4014 HST has been formulated for see through storage tanks for automotive fluids. Typical applications include reservoir bottles for brake oil, transmission fluid, engine coolant, and power steering fluid.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
Features	Good dimensional stability		
	Good chemical resistance		
	Definition, high		
	Thermal Stability		
Uses	Lawn and Garden Equipment		
	Parts under the hood of a car		
Appearance	Translucent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.30	%	ASTM D955
Transverse flow	0.50	%	ASTM D955
Water Absorption (24 hr)	0.95	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	9450	MPa	ASTM D638
Tensile Strength <sup>2</sup>	178	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break)	10	%	ASTM D638
Flexural Modulus <sup>4</sup>	8220	MPa	ASTM D790
Flexural Strength <sup>5</sup>	210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	170	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	220	°C	ASTM D648
1.8 MPa, not annealed	210	°C	ASTM D648
Melting Temperature	222	°C	DSC

#### Additional Information

The value listed as Melting Point DSC, was tested in accordance with ASTM D789.

#### NOTE


1.	51 mm/min
2.	50 mm/min
3.	50 mm/min
4.	50 mm/min
5.	50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT