

S&E; PVC GGT-1013

Polyvinyl Chloride + PUR
S&E; Specialty Polymers, LLC

Message:
Dull, high quality for outsoles; good stitchability; contains vanilla odorant

General Information			
Uses	Footwear		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	61		ASTM D2240
Shaw A, 15 seconds	55		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	10.0	MPa	ASTM D412
Tensile Elongation (Break)	450	%	ASTM D412
Additional Information			

Suggested Stock Temperature: 340-360°Fross Flex, ASTM D1052, -20°F: 30000+

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

