PermaStat® 2700-50A

Styrenic Thermoplastic Elastomer RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue' $\,$

The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade.

General Information					
Additive	Antistatic property				
Features	Electrostatic discharge protection				
	Antistatic property				
RoHS Compliance	Contact manufacturer				
Appearance	Black				
	Natural color				
Forms	Particle				
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.938	g/cm³	ASTM D792		
Molding Shrinkage - Flow (3.18 mm, Injection Molded)	0.80 - 1.5	%	ASTM D955		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	50		ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	4.00	MPa	ASTM D412		
Tensile Elongation (Break)	1000	%	ASTM D412		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (3.18 mm, Injection Molded)	No Break		ASTM D256		
Unnotched Izod Impact (3.18 mm)	No Break		ASTM D4812		
Electrical	Nominal Value	Unit	Test Method		
Surface Resistivity	1.0E+11	ohms	ASTM D257		
Volume Resistivity	1.0E+10	ohms·cm	ASTM D257		
Additional Information					
Static Decay MIL-PRF-81705D, FTMS-404	46.1: <2 sec				
Injection	Nominal Value	Unit			
Rear Temperature	160 - 191	°C			
Middle Temperature	160 - 191	°C			
Front Temperature	160 - 191	°C			

Mold Temperature	16.0 - 66.0	°C	
Injection Pressure	34.0 - 69.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

