# CP PRYME® Polycarbonate PC100R

## Polycarbonate

Chase Plastics Services Inc.

#### Message:

CP PRYME® Polycarbonate PC100R is a polycarbonate (PC) product. It is available in North America. Features include:

mold release agent excellent release agent

General Information

Additive demoulding

Features Good demoulding performance

Appearance	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	64.1	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	100	%	ASTM D638
Flexural Modulus (23°C)	2280	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	880	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	129	°C	ASTM D648

Melt Flow Rate, ASTM D1238, 300°C/10 Kg: 10 to 14 g/10 minNotched Izod Impact, ASTM D256, 23°C: 16 to 17 ft-lb/in

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Additional Information

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

