

OP - PC - Unfilled 912-FDA

Polycarbonate
Oxford Polymers

Message:

OP-PC-Unfilled 912-FDA is a polycarbonate (PC) material. This product is available in North America and is processed by injection molding.
The main features of OP-PC-Unfilled 912-FDA are:
flame retardant/rated flame
accessible food
OP-PC-Unfilled 912-FDA's typical application areas are: food contact applications

General Information			
Features	Medium liquidity		
	Compliance of Food Exposure		
Agency Ratings	FDA Food Exposure, Not Rated		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 - 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	62.1	MPa	ASTM D638
Fracture	68.9	MPa	ASTM D638
Flexural Modulus	2310	MPa	ASTM D790
Flexural Strength	95.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (4°C)	800	J/m	ASTM D256
Dart Drop Impact	36.2	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	135	°C	ASTM D648
1.8 MPa, not annealed	129	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	V-2		UL 94
3.18 mm	V-2		UL 94
Additional Information			
Melt Mass - Flow Rate (MFR), ASTM D1238, 300°C/1.2kg: 9 to 13 g/10 min			
Injection	Nominal Value	Unit	

Drying Temperature	118 - 124	°C
Drying Time	3.0 - 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	271 - 293	°C
Middle Temperature	282 - 304	°C
Front Temperature	293 - 316	°C
Processing (Melt) Temp	288 - 316	°C
Mold Temperature	71.1 - 93.3	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

