

Infino WP-1100

Polycarbonate + ABS

LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Infino WP-1100 is a polycarbonate acrylonitrile butadiene styrene (PC ABS) product, which contains a glass fiber reinforced material. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Features	General		
Uses	Application in Automobile Field		
Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.21	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	41	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	0.20 - 0.50	%	ASTM D955
Transverse flow: 3.20mm	0.30 - 0.60	%	ASTM D955
Lateral flow: 3.20mm	0.30 - 0.60	%	ISO 2577
Traffic: 3.20mm	0.20 - 0.50	%	ISO 2577
Ash Content			
--	10	%	ASTM D5630
--	10	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3100	MPa	ASTM D638
--	3200	MPa	ISO 527-2/5
Tensile Strength			
Yield ²	90.0	MPa	ASTM D638
Yield	83.0	MPa	ISO 527-2/5
Fracture ³	90.0	MPa	ASTM D638
Fracture	90.0	MPa	ISO 527-2/5
Tensile Elongation			
Fracture ⁴	4.4	%	ASTM D638
Fracture	4.4	%	ISO 527-2/5
Flexural Modulus			
-- ⁵	4200	MPa	ASTM D790
-- ⁶	4300	MPa	ISO 178
Flexural Strength			
-- ⁷	120	MPa	ASTM D790
-- ⁸	135	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	55	kJ/m ²	ISO 179/1eU
23°C	58	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
-30°C, 3.18 mm	59	J/m	ASTM D256
-30°C, 6.35 mm	59	J/m	ASTM D256
23°C, 3.18 mm	69	J/m	ASTM D256
23°C, 6.35 mm	79	J/m	ASTM D256
-30°C ¹¹	6.3	kJ/m ²	ISO 180/1A
23°C ¹²	9.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	138	°C	ASTM D648
0.45 MPa, unannealed, 4.00mm	129	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	128	°C	ASTM D648
1.8 MPa, not annealed, 4.00mm	119	°C	ISO 75-2/A
Vicat Softening Temperature	131	°C	ISO 306/B50
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: 40 to 100°C	3.9E-6	cm/cm/°C	ASTM E831, ISO 11359-2
Horizontal: 40 to 100°C	6.5E-6	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature			
--	90 - 110	°C	
Hot air dryer	90 - 110	°C	
Drying Time			
--	2.0 - 4.0	hr	
Hot air dryer	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	220 - 240	°C	
Middle Temperature	240 - 250	°C	
Front Temperature	250 - 270	°C	
Nozzle Temperature	250 - 290	°C	
Mold Temperature	60 - 90	°C	
Injection Pressure	98.1	MPa	
Back Pressure	0.490 - 2.94	MPa	
Screw Speed	5 - 200	rpm	
NOTE			
1.	5.0 mm/min		

2.	5.0 mm/min
3.	5.0 mm/min
4.	5.0 mm/min
5.	2.8 mm/min
6.	2.0 mm/min
7.	2.8 mm/min
8.	2.0 mm/min
9.	Thickness: 4mm
10.	Thickness: 4mm
11.	Thickness: 4mm
12.	Thickness: 4mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

