

Varcum 29153

Phenolic

Durez Corporation

Message:

Varcum 29153 is a one-step liquid phenolic resin in a mixture of butanol and diacetone alcohol.
Baking-type, metal coating formulation.
A versatile, general purpose resin suitable for formulating coatings for a wide variety of applications.
Provides excellent resistance to solvents and acids.
Good alkali resistance.
Provides good flexibility of the cured film.
Excellent performance in baking coating formulations for metal surfaces requiring shaping of the metal after coating and curing.
For additional flexibility any compatible alkyd or vinyl resin may be added as a plasticizer. Recommended baking schedule: 10-15 minutes at 385°F. This resin is recommended for use in combination with epoxy resins for metal coatings and related applications.

General Information			
Features	Acid Resistant		
	Alkali Resistant		
	General Purpose		
	Good Flexibility		
	Solvent Resistant		
Uses	Coating Applications		
Forms	Liquid		
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity (25°C)	18000	cP	Internal Method
Post Cure Time (150°C)	0.028	hr	
Additional Information	Nominal Value	Unit	Test Method
Non-Volatile Content	68	%	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT