

# QAMAR FC21HN

Linear Low Density Polyethylene  
SPDC Ltd.

## Message:

QAMAR FC21HN is a linear low density polyethylene material. This product is available in North America, Africa and the Middle East, Europe or Asia Pacific region. The processing method is blow molded film.  
The main features of QAMAR FC21HN are:  
Antiblock software  
slide  
Transparency  
The typical application fields of QAMAR FC21HN are: movies

| General Information                       |                      |                   |             |
|-------------------------------------------|----------------------|-------------------|-------------|
| Additive                                  | Anti-caking agent    |                   |             |
|                                           | slip agent           |                   |             |
| Features                                  | smoothness           |                   |             |
|                                           | Anti-caking property |                   |             |
|                                           | General              |                   |             |
|                                           | Medium transparency  |                   |             |
| Uses                                      | Films                |                   |             |
|                                           | General              |                   |             |
| Processing Method                         | Blow film            |                   |             |
| Physical                                  | Nominal Value        | Unit              | Test Method |
| Density                                   | 0.918                | g/cm <sup>3</sup> | ASTM D4883  |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 1.0                  | g/10 min          | ISO 1872-2  |
| Hardness                                  | Nominal Value        | Unit              | Test Method |
| Durometer Hardness (Shore D)              | 55                   |                   | ISO 868     |
| Mechanical                                | Nominal Value        | Unit              | Test Method |
| Tensile Stress (Yield)                    | 9.00                 | MPa               | ISO 1872-2  |
| Tensile Strain (Break)                    | > 430                | %                 | ISO 1872-2  |
| Flexural Modulus                          | 200                  | MPa               | ISO 1872-2  |
| Films                                     | Nominal Value        | Unit              | Test Method |
| Film Thickness - Tested                   | 30                   | µm                |             |
| Tensile Modulus                           |                      |                   | ISO 527-3   |
| MD : 30 µm                                | 190                  | MPa               | ISO 527-3   |
| TD : 30 µm                                | 220                  | MPa               | ISO 527-3   |
| Tensile Stress                            |                      |                   | ISO 527-3   |
| MD: Break, 30 µm                          | 55.0                 | MPa               | ISO 527-3   |

| TD: Break, 30 μm            | 40.0          | MPa  | ISO 527-3   |
|-----------------------------|---------------|------|-------------|
| Tensile Elongation          |               |      | ISO 527-3   |
| MD: Break, 30 μm            | 550           | %    | ISO 527-3   |
| TD: Break, 30 μm            | 850           | %    | ISO 527-3   |
| Dart Drop Impact (30 μm)    | 120           | g    | ISO 7765-1  |
| Elmendorf Tear Strength     |               |      | ISO 6383-2  |
| MD : 30 μm                  | 30            | N    | ISO 6383-2  |
| TD : 30 μm                  | 160           | N    | ISO 6383-2  |
| Thermal                     | Nominal Value | Unit | Test Method |
| Brittleness Temperature     | < -70.0       | °C   | ISO 974     |
| Vicat Softening Temperature | 102           | °C   | ISO 306     |
| Melting Temperature         | 122           | °C   | ISO 11357-3 |
| Optical                     | Nominal Value | Unit | Test Method |
| Haze (30.0 μm)              | 11            | %    | ISO 14782   |
| Extrusion instructions      |               |      |             |

Resin Temperature: 200°C Blow up ratio: 2.0 Extruder: 40 mm, L/D=24 Die Diameter: 75mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

