

RTV-2 P-60

Silicone Rubber, RTV-2

Silicones, Inc.

Message:

P-60 is a high durometer, high modulus, platinum-catalyzed, RTV-2 silicone rubber designed for casting polyurethanes and epoxies. It is easy to mix and de-air, and will cure with virtually no shrinkage. The speed at which the rubber hardens can be dramatically accelerated with heat or with Pt Accelerator at room temperature. Addition-cure two-component siliconerubbers may show inhibition sensitivity. P-60 offers outstanding chemical and heat resistance and the rigidity to withstand the expansion of most polyurethane foams.

General Information			
Features	Good Chemical Resistance		
	Good Stiffness		
	High Heat Resistance		
	Low Shrinkage		
Forms	Liquid		
Physical	Nominal Value	Unit	
Specific Gravity	1.24	g/cm ³	
Thermal	Nominal Value	Unit	
Service Temperature - Cured	-51 to 343	°C	
Coverage - Cured	0.809	cm ³ /g	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Weight: 1.0		
Hardener	Mix Ratio by Volume: 14		
	Mix Ratio by Weight: 10		
Resin	Mix Ratio by Volume: 100		
Shelf Life	26	wk	
Thermoset Mix Viscosity ¹	95000 to 120000	cP	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- ²	Blue		
-- ³	Tan		
Viscosity			
-- ⁴	1.0 to 2.0	Pa·s	
-- ⁵	130 to 160	Pa·s	

Curing Time	16 to 24	hr	
Pot Life	60 to 120	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness			
Shore A ⁶	54 to 62		
Shore A ⁷	58 to 66		
Tensile Strength	5.58 to 6.83	MPa	ASTM D412
Tensile Elongation at Break	180 to 230	%	ASTM D412
Tear Strength	11.4 to 14.9	kN/m	ASTM D624

NOTE

- | | |
|----|-----------|
| 1. | Mixed |
| 2. | Activator |
| 3. | Base |
| 4. | Activator |
| 5. | Base |
| 6. | 1 Day |
| 7. | 7 Days |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT