

ESTOPLAST ZK 6002RD01

Polycarbonate

Ester Industries Ltd.

Message:

Polycarbonate - Unfilled , Red

Automobile : Indicator light shielding Parts

Electrical & Electronic: Switches part and Light Shielding

General Information			
Additive	demoulding		
	UV stabilizer		
Features	UV Stabilized		
	High liquidity		
	Good demoulding performance		
Uses	Electrical/Electronic Applications		
	Switch		
	Application in Automobile Field		
RoHS Compliance	RoHS compliance		
Appearance	Red		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	22	g/10 min	ASTM D1238
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	65.0	MPa	ASTM D638
Tensile Elongation (Break)	40	%	ASTM D638
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	600	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	130	°C	ASTM D648
1.8 MPa, not annealed	120	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	> 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	15	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.2 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	265 - 275	°C	
Middle Temperature	285 - 295	°C	
Nozzle Temperature	280 - 290	°C	
Processing (Melt) Temp	280 - 290	°C	
Mold Temperature	60 - 80	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

