

ELASTOSIL® R plus 4001/60

Silicone
Wacker Chemie AG

Message:

- Silicone Rubber, HTV
- Molded Parts, Technical, Plastics and Rubber Processing
- Molded Parts, Food Contact, Plastics and Rubber Processing
- Spark Plugs Boots, Automotive & Transportation
- Molded Parts, Automotive, Plastics and Rubber Processing
- Technical Textiles, Technical Textiles
- Coating of Fabrics and Textiles, Technical Textiles
- Molded parts; tap water and wastewater contact, Plastics and Rubber Processing

General Information	
Features	Food Contact Acceptable
	General Purpose
Uses	Automotive Applications
	Automotive Under the Hood
	Gaskets
	Membranes
	Potable Water Applications
	Seals
	Transparent Parts
Processing Method	Coating
	Compression Molding
	Press Molding

Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.14	g/cm³	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	60		DIN 53505
Tensile Strength	11.0	MPa	DIN 53504
Tensile Elongation at Break	610	%	DIN 53504
Compression Set	16	%	DIN ISO 815-B
Tear Strength	30.0	kN/m	ASTM D624B
Rebound Resilience	61	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT