

# ExxonMobil™ LLDPE LL 6201 Series

Linear Low Density Polyethylene Resin

ExxonMobil Chemical

## Message:

LL 6201 series is a high-fluidity linear low-density polyethylene grade, with a unique combination of excellent processability and good production performance. Compared with low density polyethylene products, the parts made of LL 6201 have good gloss and have advantages in toughness, environmental stress cracking resistance, hardness and heat deformation resistance.

General Information			
Additive	LL 6201XR: heat stabilizer		
	LL 6201RQ: heat stabilizer		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	50	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (10% Igepal)	7.00	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	11.0	MPa	ISO 527-2/1A/50
Tensile Strain			ISO 527-2/1A/50
Yield	17	%	ISO 527-2/1A/50
Fracture	> 100	%	ISO 527-2/1A/50
Flexural Modulus	290	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	47	kJ/m <sup>2</sup>	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	91.0	°C	ISO 306
Additional Information			

成型性能是使用基于 ISO 1872-2 标准的 4 mm(157.5 mil)厚注塑成型试样测定的.ESCR 是基于 2 mm(78.7 mil)厚的模压板所测定.

Legal statement
-----------------

本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT