

MIDILENA I XCF-2

Low Density Polyethylene
ROMPETROL PETROCHEMICALS S.R.L.

Message:
Applications: 25 to 80 Micron films for: General purpose film, form-fill-seal packaging, think-gauge films and bags, packaging of textile products

General Information			
Features	Homopolymer		
Uses	Bags		
	Film		
	Textile Applications		
	Thin-walled Packaging		
Agency Ratings	EU 2002/72/EC		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ISO 1183
Apparent Density	0.55	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	10.5	MPa	
Break	12.5	MPa	
Tensile Strain (Break)	600	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT