

Nipol® LX855EX1

Latex
Zeon Corporation

Message:

Acrylate latex
Characteristics
Harder than LX851 with good resistance to washing and dry cleaning. Extremely low formaldehyde.
Applications
Wet tissues, food tray mats, and ventilation filters.
Glass fibers.

General Information			
Features	Copolymer		
	Crosslinkable		
Uses	Filters		
Physical	Nominal Value	Unit	
Solution Viscosity	20	mPa·s	
pH	6.5		
Surface Tension	28	mN/m	
Total Solids	45	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	36.0	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT