Axiall PVC 8864

Flexible Polyvinyl Chloride Axiall Corporation

Message:

General purpose PVC extrusion compound recommended for applications that require UV and fungus resistance.

General Information			
Features	Fungus Resistant		
	General Purpose		
	Good UV Resistance		
Uses	General Purpose		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	86		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
	14.1	MPa	
100% Strain	8.48	МРа	
Tensile Elongation (Break)	320	%	ASTM D638
Extrusion	Nominal Value	Unit	
Melt Temperature	182	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

