Europrene® SOL TH 2315

Styrene Ethylene Butylene Styrene Block Copolymer

Versalis S.p.A.

Message:

Europrene® SOL TH 2315 is a linear block copolymer obtained by selective hydrogenation of styrene-butadiene-styrene block copolymers. The polymer is based on styrene and ethylene/butylene, where bound styrene content is 32%wt. A non-staining, TNPP free antioxidant system is added during the production process.

Key Features

Europrene® SOL TH 2315 is a linear triblock copolymer of high molecular weight, specifically designed to be formulated with high contents of processing oils and mineral fillers. The grade is characterized by excellent mechanical properties and ageing resistance.

Main Applications

Europrene
© SOL TH 2315 is designed for technical compound applications. High performance compounds based on Europrene
® SOL TH 2315 show excellent elastic and tensile characteristics, in a wide range of flowability and hardness.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Block Copolymer		
	High Elasticity		
	High Molecular Weight		
Uses	Compounding		
	Pellets		
Forms			
Processing Method	Compounding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	< 1.0	g/10 min	ASTM D1238
Bound Styrene	32.0	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	68		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	3.50	MPa	ASTM D412
Tensile Strength	25.0	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Additional Information	Nominal Value	Unit	
Shelf Life	24	month	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

