

# LARIPUR® LPR 9025

Thermoplastic Polyurethane Elastomer (Polyester)

COIM S.p.A.

Message:

LARIPUR® LPR 9025 is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) material. This product is available in North America, Latin America or Europe. The processing method is extrusion or injection molding.

LARIPUR®The main features of LPR 9025 are:

- Good toughness
- Good tear strength
- good weather resistance
- chemical resistance
- Wear-resistant

General Information			
Features	Low Temperature Flexibility		
	Good tear strength		
	Good wear resistance		
	Good chemical resistance		
	Good weather resistance		
	Good toughness		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain	5.80	MPa	ASTM D412
100% strain	7.30	MPa	ASTM D412
300% strain	24.1	MPa	ASTM D412
Tensile Strength (Break)	60.1	MPa	ASTM D412
Tensile Elongation (Break)	540	%	ASTM D412
Tear Strength	106	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 70 hr	24	%	ASTM D395
70°C, 22 hr	45	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	104	°C	ASTM D1525

#### Additional Information

Abrasion loss, DIN 53516: 30 mm<sup>3</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

