

# Kemcor HD 224R

High Density Polyethylene

Qenos Pty Ltd

## Message:

This material is a HDPE recycled from post consumer waste including dairy, juice and cream bottles.

General Information	
Recycled Content	Yes
Features	Good Impact Resistance
	Recyclable Material
Forms	Pellets
Processing Method	Blow Molding
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	700	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	29.0	MPa	
Break	16.0	MPa	
Tensile Elongation (Break)	400	%	ASTM D638
Injection	Nominal Value	Unit	
Processing (Melt) Temp	165 to 175	°C	
Screw Speed	50 to 55	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT