

REXtac® APAO RT 1315

Polyalphaolefin

Huntsman Corporation

Message:

REXtac® APAO RT 1315 is a poly α -olefin (PAO) product. It is available in North America. REXtac® APAO RT 1315 applications include food contact applications and coating applications. The main characteristics are: copolymer.

General Information			
Features	Copolymer		
Uses	Laminate		
Agency Ratings	FDA 21 CFR 175.105		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.858	g/cm ³	ASTM D792
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-28.9	°C	DSC
Fill Analysis	Nominal Value	Unit	
Melt Density (191°C)	0.740	g/cm ³	
Additional Information			

Melt Viscosity, ASTM D3236, 300°F: 4300 cpsMelt Viscosity, ASTM D3236, 325°F: 2800 cpsMelt Viscosity, ASTM D3236, 350°F: 2000 cpsMelt Viscosity, ASTM D3236, 375°F: 1500 cpsMelt Viscosity, ASTM D3236, 400°F: 1100 cpsNeedle Penetration, ASTM D1321, 25°C: 2.5 mmSoftening Point by Ring and Ball, ASTM E28: 280°FFlashpoint, COC, ASTM D93: >450°FOpen Time, Kraft/Kraft, 25°C, Huntsman Method: 20 seconds

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT