ALTECH® PA6 C 2030/100 GF30

Polyamide 6

ALBIS PLASTIC GmbH

Message:

ALTECH® PA6 C 2030/100 GF30 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Typical application: Housings.

Characteristics include:

REACH Compliant

RoHS Compliant

Good Mold Release

Heat Stabilizer

High Flow

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Mold Release		
	Heat Stabilized		
	High Flow		
Uses	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8500	МРа	ISO 527-2
Tensile Stress	115	МРа	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	7800	МРа	ISO 178
Flexural Stress	220	МРа	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	9.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	45	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	200	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 12	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	270 to 290	°C	

Mold Temperature 80.0 to 100 °C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

