

LNP™ THERMOCOMP™ SF00A compound

Polyamide 12

SABIC Innovative Plastics

Message:

LNP THERMOCOMP SF00A is a compound based on Nylon 12 resin containing 50% Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound SF-100-10

Product reorder name: SF00A

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.20 to 0.40	%	
Across Flow : 24 hr	0.80 to 1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12800	MPa	ASTM D638
--	12300	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	121	MPa	ASTM D638
Yield	113	MPa	ISO 527-2/5
Break ³	121	MPa	ASTM D638
Break	113	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	1.8	%	ASTM D638
Yield	1.5	%	ISO 527-2/5
Break ⁵	1.8	%	ASTM D638
Break	1.5	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	8930	MPa	ASTM D790
-- ⁷	11.0	MPa	ISO 178
Flexural Strength ⁸			ASTM D790
Yield, 50.0 mm Span	148	MPa	
Break, 50.0 mm Span	143	MPa	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	97	J/m	ASTM D256
23°C ⁹	1.8	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			

23°C	580	J/m	ASTM D4812
23°C ¹⁰	31	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy	16.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	176	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	166	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	176	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.12 to 0.20	%	
Rear Temperature	216 to 227	°C	
Middle Temperature	221 to 232	°C	
Front Temperature	227 to 238	°C	
Processing (Melt) Temp	227 to 238	°C	
Mold Temperature	71.1 to 82.2	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*4		
10.	80*10*4		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT