

ARC ARC2200

Polycarbonate
ARC Resin Corporation

Message:
ARC ARC2200 is a Polycarbonate (PC) material. It is available in North America. Primary attribute of ARC ARC2200: Flame Rated.

General Information			
Features	Medium Flow		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C, 6.35 mm)	2280	MPa	ASTM D638
Tensile Strength (23°C, 6.35 mm)	58.6	MPa	ASTM D638
Tensile Elongation (Break, 23°C, 6.35 mm)	130	%	ASTM D638
Flexural Modulus (23°C, 3.18 mm)	2340	MPa	ASTM D790
Flexural Strength (23°C, 3.18 mm)	86.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	750	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ¹ (1.8 MPa, Unannealed, 6.35 mm)	129	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.52 mm, All	V-2		
2.29 mm, All	V-2		
NOTE			
1.	0.250" x 0.5" x 5" bar		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT