ADEKA EPR-4923

Epoxy; Epoxide

Adeka Corporation

Message:

Chelate modified type, High adhesion

General Information		
Features	Good Adhesion	
Physical	Nominal Value	Unit
Chlorine Content	0.2	wt%
Chlorine Content - Saponifiable	0.0100	wt%
Color - G	< 3.0	
Epoxy Equivalent	175 g/ep	
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	2700	сР

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

