

Triapol® Blends C3 K55 CNZ0062 BS301

Polycarbonate + ABS

Petropol Industry and Trade of Polymers LTDA

Message:

Polymer blend PC / ABS, in color gray mainly characterized by its resistance to impact and temperature, have good dimensional stability and electrical insulation property.

General Information			
Features	Electrically Insulating		
	Good Dimensional Stability		
	Good Impact Resistance		
Appearance	Grey		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>PC + ABS<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/5.0 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (Equilibrium)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ASTM D638
Tensile Strength	59.0	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2700	MPa	ASTM D790
Flexural Strength	91.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	450	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	93.0	°C	ASTM D648
Vicat Softening Temperature	120	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	30	kV/mm	ASTM D149
Comparative Tracking Index	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	110	°C
Drying Time	4.0	hr
Processing (Melt) Temp	240 to 280	°C
Mold Temperature	70.0 to 100	°C

NOTE

1.
- Rate A (50°C/h)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT