

POLIMAXX 1111JXTA8

Polypropylene Homopolymer
IRPC Public Company Limited

Message:

1111JXTA8 is a PP Homopolymer with 40% talcum filler for injection molding process. It features medium melt flow, high flexural modulus and high heat resistance. It is suitable for auto parts and electrical appliances.

General Information			
UL YellowCard	E132283-222097		
Filler / Reinforcement	Talc,40% Filler by Weight		
Features	High Heat Resistance		
	High Stiffness		
	Homopolymer		
	Medium Flow		
Uses	Appliance Components		
	Automotive Applications		
	Electrical/Electronic Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 584 mm)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	36.3	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	5880	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	53.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	2.94	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	147	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	

Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	190 to 240	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

