

INLUBE PPSLTF10

Polyphenylene Sulfide
Infinity LTL Engineered Compounds

Message:
10% PTFE LUBRICATED, LINEAR POLYPHENYLENE SULFIDE

General Information			
Additive	PTFE Lubricant (10%)		
Features	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.1 to 1.3	%	ASTM D955
Water Absorption (Equilibrium)	0.040	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	37.9	MPa	ASTM D638
Tensile Elongation (Break)	1.0 to 2.0	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	37	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	135	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	316 to 332	°C	
Mold Temperature	135 to 177	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	7.6E-3 to 0.013	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

