

ELASTOSIL® R 401/90

Silicone
Wacker Chemie AG

Message:

Silicone Rubber, HTV
Extrudates, Technical, Plastics and Rubber Processing
Extrudates, food contact, Plastics and Rubber Processing
Extrudates, Automotive, Plastics and Rubber Processing
Molded Parts, Automotive, Plastics and Rubber Processing
Molded Parts, Food Contact, Plastics and Rubber Processing
Molded Parts, Technical, Plastics and Rubber Processing

General Information	
UL YellowCard	E75704-101818639
Features	Food Contact Acceptable
	General Purpose
Uses	Automotive Applications
	Compounding
	Gaskets
	Profiles
	Seals
	Valves/Valve Parts
	Wire & Cable Applications
Processing Method	Compression Molding
	Extrusion
	Press Molding
	Profile Extrusion

Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.22	g/cm³	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	85		DIN 53505
Tensile Strength	8.00	MPa	DIN 53504
Tensile Elongation at Break	260	%	DIN 53504
Compression Set	50	%	DIN ISO 815-B
Tear Strength	23.0	kN/m	ASTM D624B
Rebound Resilience	58	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

