# SILVER® ABS 323G20

#### Acrylonitrile Butadiene Styrene

Guangdong Silver Age Sci & Tech. Co., Ltd

#### Message:

SILVER® Modified ABS is applied to many fields, such as computer fittings, OA equipment and fittings, appliance crust and electronic fittings. In addition, the custom—made products should be developed by buyers 'requirements in order to meet special usage.

Glass Fiber Reinforced ABS

Characteristics:

easy molding, high rigidity, good dimension stability, UL-94 VO/1.5

Application:

trump case, fan crust, camera crust

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Dimensional Stability		
	Good Moldability		
	High Rigidity		
Uses	Camera Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	85.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	3.0	%	ASTM D638
Flexural Modulus <sup>3</sup>	5000	MPa	ASTM D790
Flexural Strength <sup>4</sup>	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	10.0	kJ/m²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	99.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 to 230	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	5.5 mm/min		
4.	5.5 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

