

# NEFTEKHIM PE 4133Q (33403)

Medium Density Polyethylene

Nizhnekamskneftekhim Inc.

Message:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts.

Stabilization recipe: antacid, antioxidant, thermostabilizer, dispersing agent..

Application: cast stiff film, diaper backing film.

Technical requirements: TU 2211-145-05766801-2008

General Information			
Additive	Acid Neutralizer		
	Antioxidant		
	Heat Stabilizer		
Features	Acid Resistant		
	Antioxidant		
	Dispersible		
	Heat Stabilized		
Uses	Cast Film		
	Film		
	Sanitary Products		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.931 to 0.935	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.8 to 3.4	g/10 min	ASTM D1238
Gel Content <sup>1</sup>	100	pcs/m <sup>2</sup>	
Melt Flow Ratio - MFR 21.6 kg/MFR 2.16 kg	< 30.0		ASTM D1238
NOTE			
1.	p.6 attachment A TU 2211-145-05766801		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

