

# INFUSE™ 9507

Olefin Block Copolymer

The Dow Chemical Company

Message:

INFUSE™ 9507 Olefin Block Copolymer is a high performance olefin block copolymer that has excellent flow characteristics and performs well in a wide range of general purpose thermoplastic elastomer applications, such as injection molding and profile extrusion. INFUSE 9507 provides outstanding haptics in over molding applications with polypropylene (PP) and Polyethylene (PE). In addition its lower density can help control resin and production costs, while reducing the weight of end products.

- Main Characteristics:
- High upper service temperature performance
  - Highly flexible with good elastic recovery
  - Fast set up times for processability
  - General purpose elastomer
  - Excellent for compounds and blends
  - Talc dusted
  - Complies with
  - EU, No 10/2011
  - U.S. FDA FCN 424
- Consult the regulations for complete details

General Information			
Agency Ratings	EU No 10/2011		
	FDA FCN 424		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.866	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, Compression Molded)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant (Compression Molded)	1.49	MPa	ASTM D638
Tensile Strength (Break, Compression Molded)	2.89	MPa	ASTM D638
Tensile Elongation (Break, Compression Molded)	1200	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	7.00	MPa	ASTM D412
Tensile Elongation (Break)	1900	%	ASTM D412
Tear Strength	22.0	kN/m	ASTM D624
Compression Set			ASTM D395
21°C	22	%	
70°C	70	%	

Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	119	°C	Internal Method
TMA <sup>1</sup> (1.00 mm)	77	°C	Internal Method
NOTE			
1.	1N, 5°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

