

Rotuba CAB B9024 (13% Plasticizer)

Cellulose Acetate Butyrate

Rotuba Extruders, Inc.

Message:

Rotuba CAB B9024 (13% Plasticizer) is a cellulose acetate butyrate (CAB) product. It can be processed by injection molding and is available in North America. Rotuba CAB B9024 (Plasticizer 13%) has applications including optics/lenses, automotive industry, commercial/office supplies, consumer goods and handles.

- Features include:
- environmental protection/green
 - Good dimensional stability
 - Impact resistance
 - good weather resistance

General Information			
Features	Good dimensional stability		
	Updatable resources		
	Low temperature impact resistance		
	Good weather resistance		
	amorphous		
Uses	Handle		
	Optical applications		
	Application in Automobile Field		
	Toys		
	Stationery		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.60	%	ASTM D955
Water Absorption (24 hr)	1.4	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	24.8	MPa	ASTM D638
Fracture	34.5	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	1100	MPa	ASTM D790
Flexural Strength	32.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	370	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	68.9	°C	ASTM D648
Vicat Softening Temperature	100	°C	ASTM D1525
Injection	Nominal Value	Unit	
Processing (Melt) Temp	221	°C	
Mold Temperature	52	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

