

ARMAMID® PA CM 25-2AP

Polyamide 6

Poly Plastic

Message:

ARMAMID® PA CM 25-2AP is a Polyamide 6 (Nylon 6) product. It is available in Europe.

General Information		
Physical	Nominal Value	Unit
Density	1.34	g/cm ³
Molding Shrinkage	0.50 to 0.70	%
Water Absorption		
23°C, 24 hr	1.0	%
Saturation, 23°C	7.0	%
Equilibrium, 23°C, 50% RH	2.3	%
Mechanical	Nominal Value	Unit
Tensile Stress (Yield)	74.0	MPa
Flexural Modulus (23°C)	4800	MPa
Flexural Stress	100	MPa
Impact	Nominal Value	Unit
Charpy Unnotched Impact Strength		
-40°C	12	kJ/m ²
20°C	20	kJ/m ²
Thermal	Nominal Value	Unit
Heat Deflection Temperature (1.8 MPa, Unannealed)	70.0	°C
Melting Temperature	218	°C
Electrical	Nominal Value	Unit
Surface Resistivity		
-- 1	1.0E+13	ohms
-- 2	1.0E+15	ohms
Volume Resistivity		
-- 3	1.0E+15	ohms · cm
-- 4	1.0E+17	ohms · cm
Electric Strength		
-- 5	23 to 25	kV/mm
-- 6	16 to 20	kV/mm
Flammability	Nominal Value	Unit
Glow Wire Ignition Temperature	850	°C
Additional Information	Nominal Value	Unit
Burn Resistant Category (2.00 mm)	PX-2	

Trekingostoykost (KIT)	635.00	cm
NOTE		
1.	Wet	
2.	Dry	
3.	Wet	
4.	Dry	
5.	Dry	
6.	Wet	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT